

Woven Carbon/Aramid fabric

165 g/m², plain weave

Technical Data:

Areal weight	165 g/m ²	+/-5%
Weave	Plain weave	
yarn warp	HS-Carbon 3k Aramide Twaron 2200-1210dtex	
weft	HS-Carbon 3k, Aramide Twaron 2200-1210dtex	
Thread Count warp	3,3 ends/cm CF 1,7 ends/cm AF	
Thread Count weft	1,7 ends/cm CF 3,3 ends/cm AF	
Weight distribution CF / AF warp	67 g/m ² / 22 g/m ² 41% / 13 %	
Weight distribution CF / AF weft	33 g/m ² / 43 g/m ² 20% / 26 %	
Thickness (only for information)	0,16 mm	+/-2,5%
Weight rate warp / weft	54% / 46%	
width	120 cm (100 cm)	+/-2,5%
Selvages	Weaving style LENO HM Polyester 22 tex	

Information contained in this data sheets is up-to-date and correct as at the date of issue. As we can't control or anticipate the conditions under which this product may be used, each user should review the information in specific context of the planned use. We will not be responsible for damages of any nature resulting from the use or reliance upon the information contained in this data sheet.