AIRTECH EUROPE SARL
18, ZI Haneboesch
L-4562 Differdange
LUXEMBOURG
Phone: +352 58 22 82 1
Fax: + 352 58 49 35
E-mail: sales@airtech.lu
Website: www.airtech.lu

Data Sheet

WRIGHTLON® 5200

High performance fluoropolymer release film

DESCRIPTION

Wrightlon® 5200 release film has an excellent elongation which ensures that it will conform to complex curvatures. It is capable of cure temperatures up to 260°C (500°F). This film will release from most resin systems and will provide a glossy finish when used directly on the laminate. All standard perforations are available. Please see our perforation table in this section.

BENEFITS

- Good elongation and strength reduces tearing and bridging in corners, so less rework on resin rich corners.
- Wider films reduce seams yielding faster bagging and safer cures for large parts.
- High visibility colors reduce risk of leaving film on cured parts or confusion between perforation styles.

TECHNICAL DATA

		Test method
Material type	ETFE	
Elongation at break	350 %	ASTM D 882
Tensile strength	48 MPa (7000 psi)	ASTM D 882
Maximum use temperature	260°C (500°F)	
Materials to avoid	Compatible with most resin systems	
Colour	Blue/Red/Clear/Yellow	
Storage	_{Recommended storage temperature is 5°C to 40°C (41°F to 104°F). Store indoors in original packaging, do not stack rolls on end.	

SIZES

Thickness	Width	Forms Available*
15 µm (0.0006 inch)	up to 1.22 m (48 inches)	SHT
20 µm (0.0008 inch)	up to 1.52 m (60 inches)	SHT
25 µm (0.001 inch)	up to 3.05 m (120 inches)	SHT, CF
50 µm (0.002 inch)	up to 1.52 m (60 inches)	SHT

- For more sizes, see the *Commonly Used Sizes* chart in this section.
- Custom shapes and sizes are available, please contact Airtech for more information.

SHT=Sheeting



CF=Centerfold

SUSTAINABILITY



Can be recycled



Reduce waste with lower gauge



Contains recycled materials



Recyclable packaging

NOTES

- The maximum use temperature is dependent upon the duration at maximum temperature and is process specific, Airtech recommends testing prior to use.
- Wrightlon® 5200 is available treated inside (TIS), outside (TOS), or both sides (TBS). Shelf life of Wrightlon 5200 TIS, TOS, or TBS is 18 months from date of shipment.

Last updated : 2025-10-07
Catalogue position : Release Films

As the conditions or methods of use, including storage, are beyond our control, Airtech Europe does not assume any responsibility for the performance of this material for any particular use. The material is sold "as is". Airtech Europe disclaims, and buyer waives, any and all implied warranties, including without limitation the implied warranties of merchantability and of fitness for particular use. The information contained herein represents typical properties and should not be used for specification purposes. This translation is provided for your convenience only. The official language is English and the official law is Luxembourg.